

# NAVAIR Progress in Assessing, Validating and Implementing Non-Chromate Primers

February 9, 2011

Julia Russell  
Materials Engineering  
Division



Report Documentation Page				Form Approved OMB No. 0704-0188	
Public reporting burden for the collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to a penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.					
1. REPORT DATE <b>09 FEB 2011</b>		2. REPORT TYPE		3. DATES COVERED <b>00-00-2011 to 00-00-2011</b>	
4. TITLE AND SUBTITLE <b>NAVAIR Progress in Assessing, Validating and Implementing Non-Chromate Primers</b>				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S)				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) <b>Naval Air Warfare Center, Materials Engineering Division, 22347 Cedar Point Road, Patuxent River, MD, 20670</b>				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSOR/MONITOR'S ACRONYM(S)	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT <b>Approved for public release; distribution unlimited</b>					
13. SUPPLEMENTARY NOTES <b>ASETSDefense 2011: Sustainable Surface Engineering for Aerospace and Defense Workshop, February 7 - 10, 2011, New Orleans, LA. Sponsored by SERDP/ESTCP.</b>					
14. ABSTRACT					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT <b>Same as Report (SAR)</b>	18. NUMBER OF PAGES <b>19</b>	19a. NAME OF RESPONSIBLE PERSON
a. REPORT <b>unclassified</b>	b. ABSTRACT <b>unclassified</b>	c. THIS PAGE <b>unclassified</b>			

# Overview

- Why?
- Application Areas: Status
- On-going efforts
- Implementation Strategy
- Comprehensive NC Primer Projects
- Where are we going?




# Why?

To understand the balance between corrosion protection, environmental benefits, regulatory compliance and logistics for any new coating or coating system



# NAVAIR Application Areas for Hexavalent Chromium Alternatives: Status

- Alternatives Implemented/Niche Chromate Use Remains
- Limited Implementation/Near Term Validation
- No Implementation/Very Limited Implementation



# On-going Efforts

Project/Primer	Goal
Mg-Rich Primer	Optimize primer for general use
Electrocoat Primer	Optimize, demonstrate and validate primer/process for aluminum component rework/repair
Non-Chromate, Zero VOC Coating System	Demonstrate and validate coating system for steel ground support equipment
Crosslink	Optimize and mature primer formulation for general use



# Mg-Rich Primer

- Assessing MgRP003 formulation in testing:
  - P003 performs better than 1<sup>st</sup> and 2<sup>nd</sup> generation formulations (MgRP XP406/XP417)
- Modifications have greatly improved performance
- For use in Naval environment, self-corrosion failure mechanism in accelerated (NSS/SO<sub>2</sub>) and beach environment must be understood and overcome
- NAVAIR pursuing cooperative research and development agreement (CRADA) with AkzoNobel to further improve performance to meet NAVAIR requirements




Early Akzo Nobel  
formulation after  
1056 hrs SO<sub>2</sub>



Latest version  
from Akzo Nobel  
after 1176 hrs  
SO<sub>2</sub>

# Electrocoat Primer

- Primer formula optimization in progress – NSS,  $\text{SO}_2$ , Galvanic assembly, Beach Exposure Testing
- Dem/Val location: FRC-Southwest (NAS NI)
  - Electrocoat tank installation
  - Demonstrate primer on aluminum components, such as wheel assemblies



# Non-Chromate, Zero VOC Coating System

- Current coating process for steel: grit blast & paint direct to metal
- NC/ZVOC coating system to be demonstrated at FRC-East on Navy ground support equipment
- Laboratory Testing Complete – Humidity, RSL and WTA performed at NAS PAX, GM9540P & Pull-off Adhesion performed at ARL, Beach Exposure testing conducted at Cape Canaveral by Army.

**Topcoated w/ Deft 55W002  
(85285, Ty III)**

**Primed w/ Deft 02GN084  
(23377N, Ty I)**

**Chemetall Oxsilan  
(NC Pretreatment)**


**STEEL**

# Crosslink Primer

- Previously funded through ESTCP Project #WP-200904
- 3-component primer based on promising new NC pigment package
- Crosslink partnered with Hentzen Coatings, Inc. and Wayne Pigment Corporation to optimize and mature primer formulation
- In-house  $\text{NSS}/\text{SO}_2$  testing in-progress


# NC Primer Comprehensive Evaluation: (In-house Study)

- Evaluated coatings systems made up of 5 different pretreatments and 7 different primers.
- Scribed flat panels and galvanic assemblies tested in NSS, SO<sub>2</sub>, and beach exposure
- Minitab - statistical analysis




## Main Effects: All Coatings

Data Means




**Main Effects: Best Surface Treatments, All Primers**

Data Means



## Main Effects: Best Coatings

Data Means



# Implementation Strategy

- Based on primer risk assessment
- Application Axis vs. Platform/Basing Axis
- Application Axis: Low-to-High Risk
  - 1 (L) – Composite/Fiberglass Surfaces
  - 2 (L) – Non-critical Metallic Surfaces – External Fuel Tanks, etc.
  - 3 (M) – Airframe Tie-Coat Applications
    - 3A – OML / 3B – IML – Topcoat or inspectable areas only
  - 4 (M-H) – Airframe Direct-to-Metal Applications
    - 4A – OML / 4B – IML
  - 5 (H) – Interior/Faying Surface/HS Components.



# Implementation Strategy

- Platform Axis
  - 1 (L) – Trainer Aircraft – T-45, T-34, etc.
  - 2 (M) – Land based Aircraft – KC-135, C-40, etc.
  - 3 (M-H) – Special Land – P-8, H-53, etc.
  - 4 (H) – Ship-based Aircraft – E-2, H-60, etc.
  - 5 (H) – Ship-based Aircraft – \*Specialty Coatings
    - F/A-18, EA-18G, F-35, etc.



# Comprehensive Evaluation and Transition of NC Primers

- **GOAL:** *Evaluation & dem/val of mature non-chromate primers for corrosion/environmental performance over a range of platforms and applications, starting with lower risk implementation strategies*
- Focus on Navy-specific requirements:

FRC-East	FRC-Southeast	FRC-Southwest
<ul style="list-style-type: none"><li>• <b>V22:</b> NC primer as tie coat with Type IV topcoat</li><li>• <b>H-46:</b> Ty II conversion coating w/ mature Ty II, NC primer</li><li>• Dem/val NC primer on composite components</li></ul>	<ul style="list-style-type: none"><li>• Ty I &amp; II NC coating systems, including Ty II conversion coating and NC anodize sealing</li><li>• Dem/val NC primer on composite and avionics components</li></ul>	<ul style="list-style-type: none"><li>• <b>E-2/C-2:</b> Leading Ty I NC Primer over CCC on outer moldline; if successful, implement coating system on interior/components</li><li>• Transition E-2 coating system to <b>F/A-18 Hornets</b></li></ul>



# Comprehensive Evaluation and Transition of NC Primers

- **GOAL**

- *“Top down” assessment of current NC primer technology, including coating process MRL and coating TRL*
  - *Dem/val NC primers and processes with sufficient process and coating maturity and invest in development of promising newer technologies*
- Test multiple substrates, surface conditions, exposure environments and coating combinations, comparing to CCC
- Joint service demonstration (Army, AF, USCG, USMC)



# Where are we going?

- Use the NESDI and ESTCP efforts to address the DoD Cr<sup>6+</sup> memos and anticipated new DFARS contract language and *accelerate* the transition of NC primers at DoD and OEM/Sub-contractors.
- Efforts will provide the data required to make authorization and implementation decisions, starting with low-risk applications and moving toward medium and high-risk applications as warranted by products



# Questions?

